

DESCRIPTION

- a single pack epoxy modified etch primer
- conforms to AS/NZS3750.17 Type 1, AS/NZS3884 Type 1

PRINCIPAL CHARACTERISTICS

- excellent adhesion to all common metals e.g. mild steel, zincanneal, chrome, brass, copper, lead and lead alloys, stainless steel, aluminium and galvanised iron
- may be overcoated with most low build finish types e.g. enamels, lacquers, chlorinated rubbers, polyurethanes, catalysed acrylics and epoxy coatings
- may be left up to three months before overcoating is required; ensure surface is free from chalking and contamination before top coating

COLOURS AND GLOSS

- Cream – low gloss

RECOMMENDED FILM THICKNESS (PER COAT)

	Minimum	Maximum	Typical
Dry film thickness microns	15	25	15
Wet film thickness microns	150	250	150
Theoretical spreading rate m ² /l	6.7	4.0	6.7

BASIC DATA AT 25 °C

- solids content approx.....10% by volume
- touch dry after5 minutes
- handle dry20 minutes

SURFACE PREPARATION

- remove all loose material by wire brush or mechanical sander
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning

MILD STEEL

- remove all loose material by wire brush or mechanical sander

NON FERROUS METALS, STAINLESS STEEL, ZINCALUME[®] & COLORBOND[®]

- abrade using Scotch-brite pad or wet and dry sand paper. Do not use steel wool
- substrate temperature must be at least 3 °C above dew point
- relative humidity should not exceed 85%

APPLICATION INSTRUCTIONS

- stir well before use with a flat bladed stirrer or mechanical mixer
- the temperature of the product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- adequate ventilation must be continuously maintained during application and curing
- Valspar recommends the use of coating inspection reports in compliance with AS/NZS 3894.10,11,12 refer to Information Sheet I-20 for more information
- for recommendations outside those contained in this data sheet, refer to Valspar

APPLICATION METHODS

- **AIRLESS SPRAY**
 - not recommended
- **AIR SPRAY**
 - recommended thinnerL780
 - volume of thinner10-30%
 - nozzle orifice approx.1.4-1.8mm
 - nozzle pressure0.3-0.4 MPa (50-60 psi)
- **BRUSH/ROLLER**
 - not recommended
- **CLEANING SOLVENT** L780

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Safety Data Sheet (SDS)

ADDITIONAL DATA

Overcoating Table

Overcoating interval for Duranamel PR7 when top coating with itself or compatible products

Interval	5 °C	15 °C	25 °C	35 °C
Min	5 hrs	3hrs	2hrs	1hr
Max	3 Months *			

- ensure surface is dry and free of chalking and contamination
- * if overcoating interval is exceeded, the surface must be dry and free from chalking and contamination and sufficiently roughened prior to overcoating

Curing Table

Paint temperature	5 °C	15 °C	25 °C	35 °C
Dry to handle	60 mins	40 mins	20 mins	10 mins
Full cure	2 days	1 day	1 day	1 day

- adequate ventilation must be continuously maintained during application and curing

PRECAUTIONS

- for recommendations outside those contained in this data sheet, refer to Valspar

PRODUCT COMPATIBILITY

Topcoats

- Duranamel BR22
- Epiname CF602
- Poly U400 (colours)
- Poly U750
- Paracryl IF540 (colours)

STORAGE AND PACKAGING

- shelf life at least 12 months at 25 °C
- all components shall be stored in a dry internal environment at between 5 °C and 35 °C
- packaging: 20 litres
- product line: 2001

For the most up to date information visit our website or Contact Valspar Customer Service Hotline on:

www.wattylpc.com
132 101 (Australia) or 0800 735 551 (New Zealand)



Quality
ISO 9001

Valspar is committed to quality in the design, production and delivery of its products and services. Valspar's Australian manufacturing facilities quality management systems are certified to ISO9001.

Valspar's laboratory facilities are accredited for technical competence with the National Association of Tests Authorities, Australia (NATA) and comply with the requirements of ISO/IEC 17025. Accreditation No.104 (Footscray), 1154 (Glendenning) and 931 (Kilburn).



Trademarks are the property of Valspar Paint (Australia) Pty Ltd.

1. This information, provided by Valspar Paint (Australia) Pty Ltd (hereinafter referred to as "Valspar"), is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Valspar's warranties express and implied. Valspar advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Valspar and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy and currency of its contents, Valspar does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar office before using the product(s). 4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Valspar Technical Services shall be contacted prior to commencement. VALSPAR PAINT (AUSTRALIA) PTY LTD (ABN 40 000 035 914)